



**ZAKŁADY CHEMICZNE
SPÓŁDZIELNIA PRACY
W GOLENIOWIE
POLAND**

CARD OF TECHNICAL PARAMETERS

PRODUCT: RUBBER FLOOR COVERING RIBBED

| PROPERTIES | QUANTITY/UNIT | TESTING METHODS |
|--|-------------------------------------|----------------------|
| Hardness (H) | 65±5°ShA | PN-EN ISO 868 |
| Tensile strength (TS _b) min | 2,5 MPa | PN-ISO 37:2007 |
| Resistance to heat ageing in the air at temp. 70°C after 72 hrs (SC) ΔTS _b ΔH | ±30 ±10 | PN-ISO 188:2000 |
| Fragility temperature (T _k) | -25°C | PN-ISO 812:1999 |
| Density (ρ) max | 1,65 ^Y Mg/m ³ | PN-ISO 2781+AC1:1996 |

Y – color rubber max - 1,75 Mg/m³

Zakłady Chemiczne Spółdzielnia Pracy 72-100 Goleniów ul. I Brygady Legionów 1/3
e-mail: sprzedaz@gumagoleniow.pl
www.gumagoleniow.pl

Annex no. 1 to TCA 2/2016